










## METHOD FOR MAKING AlSiMgCu ALLOY PRODUCTS HAVING ENHANCED INTERCRYSTALLINE CORROSION RESISTANCE

**Patent number:** WO9612829  
**Publication date:** 1996-05-02  
**Inventor:** BECHET DENIS (FR); WARNER TIMOTHY (FR)  
**Applicant:** PECHINEY RHENALU (FR); BECHET DENIS (FR);  
WARNER TIMOTHY (FR)  
**Classification:**  
- **international:** C22F1/05; C22C21/08; C22F1/057  
- **european:** C22C21/08; C22F1/05; C22F1/057  
**Application number:** WO1995FR01412 19951024  
**Priority number(s):** FR19940013047 19941025

**Also published as:**

 EP0787217 (A1)  
 US5858134 (A1)  
 FR2726007 (A1)  
 EP0787217 (B1)

**Cited documents:**

 US4614552  
 FR2360684  
 US4589932  
 EP0173632  
 US4424084  
more >>

[Report a data error here](#)

**Abstract of WO9612829**

A method for making high-strength rolled or extruded AlSiMgCu aluminium alloy products desensitised to intercrystalline corrosion, comprising a step of casting a plate or billet having the following composition: Si 0.7-1.3 %, Mg 0.6-1.1 %, Cu 0.5-1.1 %, Mn 0.3-0.8 %, Zr < 0.20 %, Fe < 0.30 %, Zn < 1 %, Ag < 1 %, Cr < 0.25 %, others < 0.05 % each and < 0.15 % in all, with the balance being aluminium and Mg/Si < 1; a homogenising step at 470-570 DEG C; a hot and optionally cold working step; solution treatment at 540-570 DEG C; a hardening step; and a tempering step including at least one temperature plateau at 120-250 DEG C, preferably 165-220 DEG C, the overall process length measured in equivalent time at 175 DEG C being 30-300 hours. A product having the composition given above and a conductivity, when desensitised to intercrystalline corrosion, at least 0.5 MS/m higher than in state T6, is also disclosed. Such products are particularly suitably for making structural members for aircraft fuselages or rail or road vehicles.

---

Data supplied from the **esp@cenet** database - Worldwide